



TECHNICAL DATA BLOCKOUT

COATED MATTE BLOCKOUT (610gr/ m²), FR

| Item | Unit | Value | | Test Method |
|---------------------------------------|--|-----------|------|---------------------------------|
| Base Fabric | Denier | 500DX500D | | (High tenacity yarn) 100%PES |
| Construction | Weaving/inch | 28X28 | | / |
| Weight of fabric | Gsm/m ² | 122±10 | | DIN53352 BS3424 Method5B |
| Weight of PVC | Gsm/m ² | 488±10 | | DIN53352 BS3424 Method5B |
| Total weight | Gsm/m ² | 610±20 | | DIN53352 BS3424 Method5A |
| Thickness | mm | 0.48±0.02 | | DIN EN ISO 2286-3 |
| Width | cm | Up to 320 | | / |
| Tensile Strength | N/5cm | Warp | 1850 | DIN53352 BS3424 |
| | | Weft | 1550 | |
| Tearing Strength | N | Warp | 235 | DIN53356 BS3424 |
| | | Weft | 220 | |
| Adhesion | N/5CM | 80 | | DIN53357 BS3425 Method9B |
| Temperature Resistance | °C | -20~70 | | DIN53357 BS3425 Method10 |
| Lacquering | If you need, we can lacquer with: 3555 (Acrylic), 3483 (Acrylic), 7584 (PVDF) | | | |
| Flammability | We can reach: B1, B2, M2, NFPA701, DIN75200, etc. | | | |
| LOW CADMIUM & HEAVY METALS | We can reach: EN71-3 | | | |
| Conclusions and Announcements | Declaration by Tuplex: Please choose Tuplex products suitably according to relative provisions or industrial standards. Tuplex bears the responsibility for the specified technical and performance data on this page only. Tuplex is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable) | | | |