



TECHNICAL DATA GLP001

LAMINATED MATTE BACKLIT 150Z (510gr/ m²)

Item	Unit	Value	Test Method	
Base Fabric	Denier	300DX500D	(Domestic Polyester yarn) 100%PES	
Construction	Weaving/inch	18x12	/	
Weight of fabric	Gsm/m ²	55±5	DIN53352 BS3424 Method5B	
Weight of PVC	Gsm/m ²	455±5	DIN53352 BS3424 Method5B	
Total weight	Gsm/m ²	510±10	DIN53352 BS3424 Method5A	
Thickness	mm	0.39±0.02	DIN EN ISO 2286-3	
Width	cm	102---320	/	
Tensile Strength	N/5cm	Warp	635	DIN53352 BS3424
		Weft	450	
Tearing Strength	N	Warp	125	DIN53356 BS3424
		Weft	105	
Adhesion	N/5CM	60	DIN53357 BS3425 Method9B	
Temperature Resistance	°C	-20~70	DIN53357 BS3425 Method10	
Lacquering	None			
Flammability	We can reach: B2, DIN75200			
LOW CADMIUM & HEAVY METALS	We can reach: EN71-3			
Conclusions and Announcements	Declaration by Tuplex: Please choose Tuplex products suitably according to relative provisions or industrial standards. Tuplex bears the responsibility for the specified technical and performance data on this page only. Tuplex is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)			