

## PRODUCT DATA SHEET



# Avery® Intermediate Wrapping Film

Powered by Easy Apply Technology

issued: 19/11/2007

### Introduction

Avery Intermediate Wrapping Film is a high quality calendered film designed for use in fleetmarking and corporate identification applications providing enhanced ease-of-use during application.

Entrapped air can easily be removed without the need to punch the face film. The easy-to-apply feature offers the benefits of faster wrapping of vehicles. Avery Intermediate Wrapping Film is recommended for use on flat to slightly curved surfaces.

### Description

Facefilm : 70 micron polymeric plasticised vinyl film  
Adhesive : permanent, transparent acrylic based with Easy Apply Technology  
Backing paper : two sides polyolefine coated kraft paper, 150 g/sqm

### Conversion

- Product is designed primarily for wrapping purposes and is easy to size by manual cutting during application.

### Features

- Excellent application characteristics: positionable adhesive, allowing easy removal of entrapped air.
- Slow adhesion build up permits corrections during application.
- Time saving due to ease of application.
- Film application without the use of application tape.
- Excellent dimensional stability.
- Product width up to 1,52m.
- Excellent outdoor durability, humidity and saltspray resistance.
- Excellent removability after the completion of the period of use.

### Recommendations for use

- Large fleet wrapping on flat or slightly curved surfaces.
- Corporate identity enhancement



[www.averygraphics.com](http://www.averygraphics.com)

Graphics Division  
Rijndijk 86, P.O. Box 118  
2394 ZG Hazerswoude – The Netherlands  
Tel +31 71 3421500 – Fax +31 71 3421538

**Physical properties**

<b>Features</b>	<b>Test method<sup>1</sup></b>	<b>Results</b>
Caliper, facefilm	ISO 534	70 micron
Caliper, facefilm + adhesive	ISO 534	100 micron
Dimensional stability	DIN 30646	0,30 mm. max
Adhesion, initial	FINAT FTM-1, stainless steel	300 N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel	400 N/m
Flammability		self-extinguishing
Accelerated ageing	SAE J 1960, 1500h exposure	No negative impact on film performance
Shelf life	Stored at 22° C/50-55 % RH	2 years
Durability <sup>2</sup>	Vertical exposure	
Black & White		7 years
Colours		5 years
Metallics		3 years

**Temperature range**

<b>Features</b>	<b>Results</b>
Application temperature	Minimum: +10° C
Temperature range	- 40° to + 100° C

**Chemical resistance**

<b>Features</b>	<b>Test method<sup>1</sup></b>	<b>Results</b>
Humidity resistance	120 hours exposure	No effect
Saltspray resistance	120 hours exposure	No effect
Water resistance	48 hours immersion	No effect
Chemical resistance	applied to aluminium: 1 hour diesel oil immersion 4 hours antifreeze immersion	No effect No effect

**Important**

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change.

**Warranty**

Avery® branded materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give any guarantee, warranty, or make any representation contrary to the foregoing. All Avery® branded materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**1) Test methods**

More information about our test methods can be found on our website.

**2) Durability**

The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.

