



## PVC COATED TARPAULIN

### DATA SHEET Tuplan 630 gr

		Testing Method
Width	250-320 cm 98.4 - 126 inch	
Base Fabric	100%PES 1100 Dtex 7x7	DIN EN ISO 2060
Total Weight	630 g/m <sup>2</sup> 18.5 OZ/YD <sup>2</sup>	DIN EN ISO 2286-2 BS 3424 Method 5A
Composition Fabric	160 g/m <sup>2</sup>	DIN EN ISO 2286-2 BS 3424 Method 5B
Composition Coating	4.7 OZ/YD <sup>2</sup> 470 g/m <sup>2</sup> 13.8 OZ/YD <sup>2</sup> PVC+Acrylic	
Lacquering	1/0	
Breaking Strength Warp	2200 N/5cm	DIN 53 354 BS 3424 Method
Breaking Strength Weft	495 LBS/2inch 1800 N/5cm 405 LBS/2inch	FS 5100 DIN 53 354 BS 3424 Method FS 5100
Tear Strength Warp	250 N	DIN 53 363 BS 3424 Method
Tear Strength Weft	56 LBS 250 N 56 LBS	FS 5134 DIN 53 363 BS 3424 Method FS 5134
Adhesion	100 N/5cm 22.5LBS/2inch	DIN 53 357 BS 3424 Method 9B FS 5970
Temperature resistance	-30°C/+70°C	DIN EN 1876-2 BS 3424 Method 10 FS 5874
Light Fastness(except white)	7-8	DIN EN ISO 877 BS 3424 Method 15
Flammability		DIN 75200 NFPA-701 CSFM Section 13115
Application	Truck Cover, Side Curtain	

All our technical characteristics are indicative

Declaration by Tuplex: Please choose Tuplex products suitably according to relative provisions or industrial standards. Tuplex bears the responsibility for the specified technical and performance data on this page only. Tuplex is not responsible for any other liability.

(The technical data on this page is calculated on average, and ±5% tolerance is acceptable)